

# CP260 2V 6Ah(20hr)



The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

## Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

## General Features


- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

## Performance Characteristics

- Nominal Voltage .....2V
- Number of cell .....1
- Design Life .....3-5 years
- Nominal Capacity 77°F(25°C)
  - 20 hour rate (0.3A, 1.75V) ..... 6Ah
  - 10 hour rate (0.55A, 1.75V) ..... 5.5Ah
  - 5 hour rate (1.04A, 1.75V) ..... 5.2Ah
  - 1 hour rate (4.83A, 1.6V) ..... 4.83Ah
- Internal Resistance
  - Fully Charged battery 77°F(25°C) ..... 5mOhms
- Self-Discharge
  - 3% of capacity declined per month at 20°C(average)
- Operating Temperature Range
  - Discharge ..... -20~60°C
  - Charge ..... -10~60°C
  - Storage ..... -20~60°C
- Max. Discharge Current 77°F(25°C) ..... 90A(5s)
- Short Circuit Current ..... 300A
- Charge Methods: Constant Voltage Charge 77°F(25°C)
  - Cycle use ..... 2.4-2.5V
  - Maximum charging current ..... 2.4A
  - Temperature compensation ..... -5.0mV/°C
  - Standby use ..... 2.25-2.3V
  - Temperature compensation ..... -3.3mV/°C

## Dimensions and Weight

- Length(mm / inch) ..... 51 / 2.01
- Width(mm / inch) ..... 33 / 1.30
- Height(mm / inch) ..... 99 / 3.90
- Total Height(mm / inch) ..... 104 / 4.09
- Approx. Weight(Kg / lbs) ..... 0.44 / 0.97











## Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	28.7	19.2	14.2	8.19	4.83	1.81	1.09	0.58	0.31
1.65V	27.1	18.2	13.6	7.87	4.66	1.76	1.09	0.58	0.31
1.70V	25.4	16.9	12.9	7.52	4.47	1.70	1.06	0.58	0.30
1.75V	24.0	15.4	12.3	7.15	4.27	1.65	1.04	0.55	0.30
1.80V	22.3	13.7	11.6	6.77	4.07	1.57	0.99	0.53	0.30

## Discharge Constant Power (Watts at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	52.4	34.0	28.0	17.2	12.2	9.64	5.24	3.78	2.29
1.65V	49.9	32.5	26.9	16.5	11.8	9.36	5.11	3.69	2.30
1.70V	47.1	30.3	25.8	15.9	11.3	9.02	4.95	3.59	2.26
1.75V	44.7	27.7	24.6	15.2	10.9	8.68	4.79	3.50	2.22
1.80V	41.7	24.7	23.3	14.5	10.4	8.31	4.58	3.34	2.13

(Note)The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values.



ISO9001:2000

MH25860

G4M19906-9202-E-16

[www.vision-batt.com](http://www.vision-batt.com)

**Shenzhen Center Power Tech. Co., Ltd.**  
 Center Power Industrial Park, Tongfu Industrial District Dapeng Town, 518120 Shenzhen, China  
 Tel: (+86-755) 8431 8088 Fax: (+86-755) 8431 8038 E-mail: sales@vision-batt.com